

7304 – Medium Silicone Sponge

Preliminary Data

7304 are closed cell silicone sponge materials. 7304 is available in 36" x 36" sheets at a variety of thickness.

Features and Benefits

- Handles temperature extremes
- Excellent gasketing material
- Very low compression set
- UV/Ozone Resistant

Specifications

- AMS 3195
- BMS 1-23

7304		
Property	Test Method	Typical Value
<i>PHYSICAL</i>		
Standard Color		Red
Density, lb./ft ³	ASTM D 1056	35
Compression Force Deflection, psi	Force measured @ 25% Deflection ASTM D 1056	6 -14 psi (medium stiffness)
Compression Set, % max.	ASTM D 1056 Test D @ 212°F (100°C), 22 hrs.	20%
Tensile Strength, psi	ASTM D 412	200 psi min
Elongation, %	ASTM D 412	150% min
Water Absorption, %	ASTM D 1056	5% max
<i>FLAMMABILITY</i>		
Flame Resistance	FMVSS302	Pass
Temperature Resistance		-103°F to +450°F

Notes:

1. Other colors available upon special request – Black, Gray & White.
2. Additional technical information is available.
3. Typical values are a representation of an average value for the population of the property. For specification values contact Rogers Corporation.
4. All values are based on preliminary test data and are currently up for review.

The information contained in this Data Sheet is intended to assist you in designing with Rogers' High Performance Foams. It is not intended to and does not create any warranties, express or implied, including any warranty of merchantability or fitness for a particular purpose or that the results shown on the Data Sheet will be achieved by a user for a particular purpose. The user should determine the suitability of Rogers' High Performance Foams for each application. The Rogers logo, The world runs better with Rogers, and BISCO are licensed trademarks of Rogers Corporation. © 2009, 2010 Rogers Corporation, All rights reserved. Printed in U.S.A., 1012-3010-PDF, Publication #180-155P