

XT/duroid® 8100

High Performance Circuit Materials



XT/duroid® 8100 woven glass reinforced thermoplastic circuit materials provide an excellent solution for printed circuit board applications used in demanding environmental conditions.

XT/duroid 8100 circuit materials are excellent for high frequency/high speed applications. Both dielectric constant and dissipation factor are stable over a wide range of frequencies.

XT/duroid 8100 is thermally stable, with a melt temperature higher than PTFE materials. The XT/duroid products possess impressive chemical and radiation resistance. These lead-free solder capable laminates are green materials which are naturally flame retardant and halogen free.

Data Sheet

FEATURES AND BENEFITS:

Stable dielectric constant and dissipation factor over a wide frequency range

- High reliability
- Uniform electrical properties over frequency

High maximum operating temperature

- Can be used in applications where high temperature stability is necessary

Excellent chemical resistance

- Ease of processing
- Resistant to solvents and reagents used to process circuit boards
- Operates in harsh chemical environments

Environmentally friendly

- Halogen-free / inherently flame retardant
- Lead-free solder capable
- Low smoke / toxicity

SOME TYPICAL APPLICATIONS:

- Flex-to-install applications
- Lightweight feed manifolds
- Semiconductor burn-in
- Conformal circuitry
- Oil and gas exploration

PROPERTIES	TYPICAL VALUES XT/duroid 8100		DIRECTION	UNITS	CONDITIONS	TEST METHOD
	0.002" 0.0508mm	0.004" 0.102mm				
Dielectric Constant, ϵ_r Process	3.54 ± 0.05	3.32 ± 0.05	Z		10 GHz/23°C	IPC-TM-2.5.5.5.1
[2] Dielectric Constant, ϵ_r Design	3.54	3.32	Z		8 GHz - 40 GHz	Differential Phase Length Model
Dissipation Factor	0.0049	0.0038	Z		10 GHz/23°C	IPC-TM-650, 2.5.5.5.1
Thermal Coefficient of ϵ_r	9	9	Z	ppm/°C	-100°C to 250°C	IPC-TM-650, 2.5.5.5.1
Copper Peel Strength	6.2	6.3		pli (N/mm)		IPC-TM-650 2.4.8
Outgassing	TBD	TBD				ASTM E-595
T260	PASS	PASS				
T288	PASS	PASS				
Flammability*	VTM-0	VTM-0				UL94
Volume Resistivity		10 ¹⁰	Z	MΩ•cm	COND A	IPC-TM-650, 2.5.17.1
Surface Resistivity		10 ⁶	X, Y	MΩ	COND A	IPC-TM-650, 2.5.17.1
Dielectric Strength	2.58	2.27	Z	KV/mil		IPC-TM-650, 2.5.6.2
Young's Modulus	11543	7853		MPa (kpsi)	RT	ASTM D638
Tensile Strength	216	190		MPa (kpsi)	RT	ASTM D638
Dimensional Stability	0.03 0.037	-0.025 -0.01	X - MD Y - CMD	mm/m (mils/ inch)	150°C Bake	IPC-TM-650 2.4.39A
Coefficient of Thermal Expansion 0 - 150°C	16.5	19	X	ppm/°C		IPC-TM-650, 2.1.41
	18	21	Y			
	57	76	Z			
Thermal Conductivity	0.3	0.3		W/m/K		ASTM C518
Moisture Absorption	0.05 0.15	0.21 0.32		%	D24/23 D48/50	IPC-TM-650 2.6.2.1 ASTM D570
Tg	172	176		°C TMA		ASTM D3850
Lead-Free Process Compatible	YES	YES				
Halogen Free	YES	YES				

*Reported UL values are preliminary and reflect anticipated results of full UL testing.

- [1] Typical values are a representation of an average value for the population of the property. For specification values contact Rogers Corporation.
 [2] The design Dk is an average number from several different tested lots of material and on the most common thickness/s. If more detailed information is required, please contact Rogers Corporation. Refer to Rogers' technical paper "Dielectric Properties of High Frequency Materials" available at <http://www.rogerscorp.com>.

Standard Thicknesses	Panel Sizes	Copper Cladding
0.002" (0.0508mm) ± 12.5% 0.004" (0.102mm) ± 12.5%	12" X 18" (305 X 457mm) 24" X 18" (610 X 457mm) Other panel sizes and thicknesses available upon request. Also available in rolls.	½ oz. (18µm) very low profile electrodeposited copper foil. Other copper cladding types available upon request.

The information in this data sheet is intended to assist you in designing with Rogers' circuit materials. It is not intended to and does not create any warranties express or implied, including any warranty of merchantability or fitness for a particular purpose or that the results shown on this data sheet will be achieved by a user for a particular purpose. The user should determine the suitability of Rogers' circuit materials for each application.

These commodities, technology and software are exported from the United States in accordance with the Export Administration regulations. Diversion contrary to U.S. law prohibited.

The Rogers' logo, Helping power, protect, connect our world and XT/duroid are trademarks of Rogers Corporation or one of its subsidiaries.
 © 2017 Rogers Corporation, Printed in U.S.A. All rights reserved.
 Revised 1305 060117 Publication #92-155

Advanced Connectivity Solutions
 100 S. Roosevelt Avenue, Chandler, AZ 85226
 Tel: 480-961-1382, Fax: 480-961-4533 www.rogerscorp.com

Helping power, protect, connect our world