

## BISCO® HT-200 SOUND BLOCK SILICONE

BISCO® HT-200 Sound Block materials are specifically designed to reduce the transmission of sound within interior spaces while inhibiting the spread of fire and smoke. The elastomeric materials use a filler technology to solve acoustic, fire, and smoke issues within a variety of markets. They are supplied in roll form, and are available with or without adhesives and supported backings to aid in your installation.

### Features and Benefits

- Flame retardant properties ensure compliance to international safety standards for Mass Transit and Aerospace.
- Filler technology reduces the spread of flame and toxic smoke during accidents, which are a leading cause of injuries.
- Sound transmission can be “tuned” by adjusting the areal density or weight of the materials. See tables for reference.
- Rubber elastomer has good tear strength with excellent resistance to compression set, UV light, moisture, and cleaning alcohols.
- Maintains properties at temperatures between -67°F and 482°F (-55°C and 250°C.)
- Available through distribution sites throughout North America, Europe, and Asia.

### Applications

- Sub-flooring for railcars
- Interior vehicle panels
- Air ducts

### Design Considerations

BISCO Sound Block may be applied and used in various forms. Please contact our Technical Service department at (800)935.2940 for further assistance or samples.

The information contained in this Data Sheet is intended to assist you in designing with Rogers’ High Performance Foams. It is not intended to and does not create any warranties, express or implied, including any warranty of merchantability or fitness for a particular purpose or that the results shown on the Data Sheet will be achieved by a user for a particular purpose. The user should determine the suitability of Rogers’ High Performance Foams for each application. The Rogers logo, The world runs better with Rogers and BISCO are licensed trademarks of Rogers Corporation. © 2005, 2006, 2009 Rogers Corporation, All rights reserved. Printed in U.S.A., 9041-0309-PDF, Publication #180-105

Sound Transmission Loss Typical of HT-200 at Various Weights					
Test Method	Typical Sound Transmission Loss Rating	Areal Density		Approx. Thickness	
		psf	kg/m <sup>2</sup>	in.	mm
ASTM E 90	29	1.50	7.32	0.150	3.81
ASTM E 90	27	1.00	4.88	0.100	2.54
ASTM E 90	25	0.75	3.66	0.075	1.91
ASTM E 90	22	0.50	2.44	0.050	1.27
ASTM E 90	16	0.25	1.22	0.025	0.64

Flame Spread, Optical Density and Oxygen Index		
Test Method	Identification	Typical Properties
ASTM E 162	Is	< 5
ASTM E 662	DS <sub>s</sub> Flaming D <sub>s</sub> Non-Flaming	< 25 < 25
ASTM D 2863	Oxygen Index, %	50
SMP-800C	Toxic Gas Emissions	Pass

You may contact a Technical Service Representative for further details.

### Installation

- Available with a pressure-sensitive adhesive on one or two sides to allow easy application to a variety of clean surfaces.
- Also available with a fiberglass backing on either side of the product at no extra charge to allow users a variety of options for installation. The fiberglass backing enhances the strength and tear resistance of the material, which allows users to mechanically attach the Sound Block to various surfaces such as carpet or steel without sacrificing the integrity and durability of the BISCO Sound Block material.

## BISCO® HT-200 SOUND BLOCK SILICONE (continued)

BISCO® Sound Block – Acoustic Sound Transmission Data – ASTM E 90 and ASTM E 413					
FREQ	0.25 PSF	0.50 PSF	0.75 PSF	1.0 PSF	1.5 PSF
	TL	TL	TL	TL	TL
100	8	15	16	19	20
125	7	12	14	14	15
160	7	12	13	17	18
200	8	12	15	16	19
250	8	14	17	19	21
315	8	13	18	19	20
400	10	15	19	20	23
500	11	16	20	22	24
630	13	19	22	24	26
800	14	21	24	26	28
1000	16	22	25	28	30
1250	17	24	27	30	33
1600	19	26	29	21	34
2000	21	27	30	33	36
2500	22	29	32	34	38
3150	23	31	34	36	40
4000	25	31	36	38	41
5000	27	32	37	40	43
<b>STC</b>	<b>16</b>	<b>22</b>	<b>25</b>	<b>27</b>	<b>29</b>

FREQ = Frequency, Hertz (cps.);

TL = Transmission Loss, dB;

STC = Sound Transmission Class

The information contained in this Data Sheet is intended to assist you in designing with Rogers' High Performance Foams. It is not intended to and does not create any warranties, express or implied, including any warranty of merchantability or fitness for a particular purpose or that the results shown on the Data Sheet will be achieved by a user for a particular purpose. The user should determine the suitability of Rogers' High Performance Foams for each application. The Rogers logo, The world runs better with Rogers and BISCO are licensed trademarks of Rogers Corporation. © 2005, 2006, 2009 Rogers Corporation, All rights reserved. Printed in U.S.A., 9041-0309-PDF, Publication #180-105