



BISCO® Silicones

High Performance Foams Division
 171 West St. Charles Road
 Carol Stream, IL 60188-2081
 Tel: 630.784.6200 / Fax: 630.784.6201
 www.rogerscorporation.com

BISCO® SILICONES CHEMICAL RESISTANCE GUIDE

BISCO® Silicone materials provide design solutions for applications in Transportation, Communication, Industrial and Medical markets. The following chemical resistance information, when used with the typical physical properties for each material, is provided to assist in assessing suitability for each application.

Results: In general, BISCO Silicone materials show excellent or very good resistance to exposure to diluted acids and bases, organic fluids and petroleum products. When immersed, the materials can exhibit moderate swelling and a reduction in properties.

RATING KEY		1	2	3	4	5
Tensile Strength & Dimensional Stability (% Change)		0-20	20-40	40-60	60-80	80-100
Compression Set (% Actual)		0-5	5.0-10	10-15.0	15+	

	BISCO® Silicone BF-1000					BISCO® Silicone HT-800 Series				
	Tensile Strength		Dimensional Stability		Compression Set	Tensile Strength		Dimensional Stability		Compression Set
SOLVENT MEDIUM	Wet	Dry	Wet	Dry	Dry	Wet	Dry	Wet	Dry	Dry
ACIDS & BASES										
10% Sulfuric acid	1	1	1	1	1	1	1	1	1	1
10% Hydrochloric acid	2	2	1	1	1	1	1	1	1	1
10% Acetic Acid	2	1	1	1	1	3	1	1	1	1
10% Sodium bicarbonate	1	1	1	1	1	1	1	1	1	1
10% Ammonia water	1	1	1	1	1	1	1	1	1	1
10% Potassium hydroxide	1	1	1	1	1	1	1	1	1	1
ALCOHOLS										
Isopropyl alcohol	2	1	1	1	1	2	1	1	1	1
Methyl alcohol	2	1	1	1	1	1	1	1	1	1
AUTOMOTIVE FLUIDS										
Gasoline	4	1	2	1	1	4	1	2	1	1
HOUSEHOLD CLEANERS										
Mr. Clean®	1	1	1	1	1	1	1	1	1	1
Fantastik®	2	1	1	1	1	1	1	1	1	1
Formula 409®	1	1	1	1	1	1	1	1	1	1
MISCELLANEOUS										
Distilled Water	1	1	1	1	1	1	1	1	1	1

See reverse for additional data.

The information contained in this data sheet is intended to assist you in designing with Rogers BISCO Silicones. It is not intended to and does not create any warranties, express or implied, including any warranty of merchantability or fitness for a particular purpose or that the results shown on the data sheet will be achieved by a user for a particular purpose. The user should determine the suitability of Rogers BISCO Silicones for each application.

The world runs better with Rogers.™

RATING KEY		1	2	3	4	5
Tensile Strength & Dimensional Stability (% Change)		0-20	20-40	40-60	60-80	80-100
Compression Set (% Actual)		0-5	5.0-10	10-15.0	15+	

SOLVENT MEDIUM	BISCO® Silicone General Purpose Solids					BISCO® Silicone Performance Solids				
	Tensile Strength		Dimensional Stability		Compression Set	Tensile Strength		Dimensional Stability		Compression Set
	Wet	Dry	Wet	Dry	Dry	Wet	Dry	Wet	Dry	Dry
ACIDS & BASES										
10% Sulfuric acid	1	1	1	1	1	1	1	1	1	1
10% Hydrochloric acid	1	1	1	1	1	1	1	1	1	1
10% Acetic Acid	1	1	1	1	1	1	1	1	1	1
10% Sodium bicarbonate	1	1	1	1	1	1	1	1	1	1
10% Ammonia water	1	1	1	1	1	1	1	1	1	1
10% Potassium hydroxide	1	1	1	1	1	1	1	1	1	1
ALCOHOLS										
Isopropyl alcohol	1	1	1	1	1	1	1	1	1	1
Methyl alcohol	1	1	1	1	1	1	1	1	1	1
AUTOMOTIVE FLUID										
Gasoline	3	1	2	1	1	2	1	2	1	1
HOUSHOLD CLEANERS										
Mr. Clean®	1	1	1	1	1	1	1	1	1	1
Fantastik®	1	1	1	1	1	1	1	1	1	1
Formula 409®	1	1	1	1	1	1	1	1	1	1
MISCELLANEOUS										
Distilled Water	1	1	1	1	1	1	1	1	1	1

Test Method: Immersion duration for 168 hours (1 week), at room temperature, followed by 48 hours (2 days) drying. Material properties evaluated were tensile strength, dimensional stability and compression set resistance.

The information contained in this data sheet is intended to assist you in designing with Rogers BISCO Silicones. It is not intended to and does not create any warranties, express or implied, including any warranty of merchantability or fitness for a particular purpose or that the results shown on the data sheet will be achieved by a user for a particular purpose. The user should determine the suitability of Rogers BISCO Silicones for each application.

Mr. Clean is a registered trademark of Procter & Gamble Co.
Fantastik is a registered trademark of S.C. Johnson & Son Inc.
Formula 409 is a registered trademark of The Clorox Co.

BISCO is a licensed trademark of Rogers Corporation.
© 2006 Rogers Corporation, Printed in U.S.A.
6040-0306-PDF, Publication #180-113