

BISCO® HT-6210 and HT-6220 SOFT SOLID SILICONE

BISCO® HT-6210 and HT-6220 are low durometer solid silicones formulated to be a transition between a firm silicone sponge and traditional medium hardness Shore A durometer material. The unique product softness is designed into the product enabling the material to solve sealing and design issues within various industrial markets. BISCO HT-6210 and HT-6220 are available in various thicknesses and manufactured in roll form to allow fabricators to easily convert the material to the proper dimensions.

Features and Benefits

- Soft and compressible for superior sealing performance
- Flexible, yet durable enough to perform under stringent conditions
- Tight thickness tolerances for greater reliability
- Wide temperature range means the material will work in harsh environments

Applications

- Underwater lighting gaskets
- Digital camera lens gasket
- Battery hatch seals

Silicone HT-6210 and HT-6220 Typical Physical Properties At 1/16" (1.59mm) thick			
Property	Test Method	Typical Value	
Thickness		0.010" (0.25 mm)	
		0.020" (0.50 mm)	
		0.031" (0.79 mm)	
		0.063" (1.59 mm)	
		0.125" (3.18 mm)	
Durometer, Pts	ASTM D 2240	10	20
Tensile, psi	ASTM D 412	250	800
Elongation, %	ASTM D 412	500	650
Tear Resistance, ppi	ASTM D 624	25	55
Compression Set, % (70 hrs @ 300°F, 25% compression)	ASTM D 395	30	30
Temperature	Rogers Internal	-80° to 425°F (-62° to 218°C)	
Continuous			
Color		Gray	Black

The information contained in this Data Sheet is intended to assist you in designing with Rogers' High Performance Foam Materials. It is not intended to and does not create any warranties, express or implied, including any warranty of merchantability or fitness for a particular purpose or that the results shown on the Data Sheet will be achieved by a user for a particular purpose. The user should determine the suitability of Rogers' High Performance Foam Materials for each application. The Rogers logo, The world runs better with Rogers. and BISCO are licensed trademarks of Rogers Corporation. © 2005, 2006, 2008 Rogers Corporation, All rights reserved. Printed in U.S.A., 8101-1008-PDF, Publication #180-091

Standard Thickness Tolerance

Standard Thickness (Inches)	Tolerance (Inches)
≤ 0.014	± 0.002
0.015 – 0.025	+0.003, -0.002
0.026 – 0.040	± 0.004
0.041 – 0.094	± 0.006
0.095 – 0.145	± 0.008

Width Tolerance

Nominal Width (Inches)	Tolerance (Inches)
0 < T ≤ 3	± 0.063
3 < T ≤ 8	± 0.094
8 < T ≤ 12	± 0.125
12 < T ≤ 18	± 0.188
18 < T ≤ 26	± 0.219
26 < T ≤ 36	± 0.250
>36	± 0.313

Notes:

1. All metric conversions are approximate.
2. Additional technical information is available.
3. Typical values are a representation of an average value for the population of the property. For specification values contact Rogers Corporation.

The information contained in this Data Sheet is intended to assist you in designing with Rogers' High Performance Foam Materials. It is not intended to and does not create any warranties, express or implied, including any warranty of merchantability or fitness for a particular purpose or that the results shown on the Data Sheet will be achieved by a user for a particular purpose. The user should determine the suitability of Rogers' High Performance Foam Materials for each application. The Rogers logo, The world runs better with Rogers. and BISCO are licensed trademarks of Rogers Corporation. © 2005, 2006, 2008 Rogers Corporation, All rights reserved. Printed in U.S.A., 8101-1008-PDF, Publication #180-091