



Advanced Circuit Materials

Advanced Circuit Materials
100 S. Roosevelt Avenue
Chandler, AZ 85226
Tel: 480-961-1382, Fax: 480-961-4533
www.rogerscorporation.com

Properties

2.5.1

RT/duroid® PTFE Based Composites Meet Flammability Requirements for Oxygen Environments

RT/duroid® 5870 laminate has been evaluated for flammability in gaseous oxygen according to the procedures outlined in MSFC-SPEC-101 (Proposed), "Flammability Requirements and Test Procedures for Materials in Gaseous Oxygen Environments", Test No. 1. Specimens without copper foil cladding at a nominal thickness of 0.015 inch (0.38mm) were granted a conditional approval as a Type 1 material for use in 6.2 psia (43 kPa abs.) oxygen environment. A Type 1 material is required to be found non-combustible when a strip is supported in a vertical position in the oxygen atmosphere with an energized ignition source at the bottom for a period of ten minutes.

The approval is conditional upon evaluation of each manufacturer's batch.

The results of the evaluation were stated in a letter from J.E. Kingsbury, Chief, Materials Division Propulsion and Vehicle Engineering Laboratory, National Aeronautics and Space Administration, George C. Marshall Space Flight Center, Huntsville, Alabama 35812. The letter was identified by file number R-P&VE-MC-68-94, and dated June 1968.

CONTACT INFORMATION:

Table with 4 columns: Location, Company Name, Telephone, and Fax. Rows include USA, Belgium, Japan, Taiwan, Korea, and Singapore.

The information in this data sheet is intended to assist you in designing with Rogers' laminates. It is not intended to and does not create any warranties express or implied, including any warranty of merchantability or fitness for a particular application. The user should determine the suitability of Rogers' laminates for each application.

These commodities, technology or software are exported from the United States in accordance with the Export Administration regulations. Diversion contrary to U.S. law prohibited.

RT/duroid® and DUROID® are licensed trademarks of Rogers Corporation.

©1982-2002 Rogers Corporation, Printed in U.S.A. All rights reserved.

1102-2.5ON

Publication #92-251