



Elastomeric Material Solutions Division
 1100 Governor Lea Road, Bear, DE 19701
 (302) 834-2100 (302) 834-4021 (Fax)
www.rogerscorp.com/arlon

PRODUCT INFORMATION SHEET

ARLON® Product Number P29514R015

PRODUCT DESCRIPTION

Design / Construction

Interleave: 0.003" Polyethylene
Side 1: Semi-cured Silicone Rubber
Substrate: Style 7727 Fiberglass



Rubber Add-On Thickness

	Value	Method
Side 1:	0.008"	Arlon SQA-TMS-003
Overall Thickness:	0.016"	Arlon SQA-TMS-003

Product Color : Red

TYPICAL PROPERTIES

Silicone Properties

	Value	Method
Tensile Strength psi	750	Arlon SQA-TMS-008
Elongation %	450	Arlon SQA-TMS-008
Durometer Shore A Points	47	Arlon SQA-TMS-014
Specific Gravity ---	1.18	Arlon SQA-TMS-024

Substrate Properties

	Value	Method
Thickness	0.008"	Arlon SQA-TMS-003
Color	Red	N/A

Product Properties

	Value	Method
Dielectric Strength volts/mil	805	Arlon SQA-TMS-020
Bond Strength (S1 to S1) lb/in	6.7	Arlon SQA-TMS-011
Total Product Weight oz/yd ²	20.2	Arlon SQA-TMS-025

SHELF LIFE & PROCESSING RECOMMENDATIONS

Product Shelf Life	3 months from date of manufacture @ 70°F
<i>Note: Shelf life is defined as the duration of time for which the product will meet the physical characteristics outlined on this page. It does not guarantee the product's usefulness in all applications.</i>	
Recommended Cure Cycle	15 minutes @ 350°F and 50 psi
Recommended Post-Cure Cycle	400°F for 2 hours
Product Operating Temperature	-70°F to 428°F

The data presented in this document represents typical values for the production material. Typical values should not be used for specification limits. Please verify that any printed hard copy of this datasheet is current by referencing: www.rogerscorp.com/arlon

The information contained in this Data Sheet is intended to assist you in designing with Rogers' ARLON Materials. It is not intended to and does not create any warranties, express or implied, including any warranty of merchantability or fitness for a particular purpose or that the results shown in this Data Sheet will be achieved by a user for a particular purpose. The user should determine the suitability of Rogers' ARLON Materials for each application. The Rogers logo, Helping power, protect, connect our world and ARLON are trademarks of Rogers Corporation or one of its subsidiaries. ©2017 Rogers Corporation, All rights reserved. Printed in U.S.A., 0717-PDF, **Publication #202-121**