



Arlon Silicones Technology

1100 Governor Lea Road, Bear, DE 19701  
1.302.834.2100 • 1.302.834.4021 (Fax)

PRODUCT INFORMATION SHEET	
<b>Arlon Part Number</b>	99760N015 (Thermabond®-II)
<b>Customer/Part Number</b>	

PRODUCT INFORMATION		
Design / Construction	Value	Tolerance
<b>Side 1:</b>	Unsupported/Uncured Rubber	
<b>Side 2:</b>	N/A	
<b>Rubber Add-On Thickness</b>	<b>Side 1:</b> .015"	+ .000/- .002
	<b>Side 2:</b> N/A	N/A
<b>Overall Thickness:</b>	.015"	+ .000/- .002
<b>Dielectric Strength, Volts/mil</b>	400	Minimum
<b>Lap Shear Strength, psi</b>	200	Minimum
<b>Shear Modulus, psi</b>	85	±5
<b>Thermal Impedance, °C/W</b>	1.28	±0.13
<b>Total Product Weight, oz/yd<sup>2</sup></b>	18.0	±1.0
<b>Interleave</b>	.001" FEP	
<b>Product Color</b>	Natural	
<b>Product Shelf Life</b>	6 months from date of manufacture @70° F ±5	
	<i>Note: Shelf life is defined as the duration of time for which the product will meet the physical requirements outlined below. It does not guarantee the product's usefulness in all applications.</i>	
<b>Recommended Cure Cycle</b>	15 minutes @280° F	
<b>Recommended Postcure Cycle</b>	N/A	
<b>Product Operating Temperature</b>	-70 to 450°F	
FLAME RETARDANCE INFORMATION		
<b>UL Recognition</b>	N/A	
<b>Flame Test Method</b>	N/A	
Flame Test Information	Value	Tolerance
<b>Flame Time, seconds</b>	N/A	N/A
<b>Glow Time, seconds</b>	N/A	N/A
<b>Char Length, inches</b>	N/A	N/A
COMPOUND INFORMATION		
Physical Property	Value	Tolerance
<b>Tensile Strength, psi</b>	N/A	N/A
<b>Elongation, %</b>	N/A	N/A
<b>Tear Strength, lb/in</b>	N/A	N/A
<b>Compression Set, %</b>	N/A	N/A
<b>Thermal Conductivity, W/m•K</b>	.45	Minimum
<b>Durometer, Shore A Points</b>	N/A	N/A
SUBSTRATE INFORMATION		
<b>Substrate Type</b>	PTFE Coated Fiberglass	
Physical Property	Value	Tolerance
<b>Thickness, in</b>	.003"	Nominal
<b>Uncoated Fabric Break Strength, lb/in</b>	N/A	N/A
<b>Warp Direction:</b>	N/A	N/A
<b>Fill Direction:</b>	N/A	N/A

The data presented in this document represents typical values for the production material.  
This data should not be used to write, or in place of, material specifications.