

ARLON® FLEX HEATER SUBSTRATE SPECIFICATION

Item Number: 44106R010
Description: Flexible Heater Substrate
Silicone Rubber Calendered onto Fiberglass

Design / Construction



Substrate: 44 Plain Weave Fiberglass (5 mil nominal)
Silicone Rubber Compound: 10 Compound
Color: Red

Interleave (Top): LDPE
Interleave (Bottom):

	<u>Rubber Add-on</u>	<u>Tolerance</u>	<u>Cure State</u>	<u>Method</u>
Side 1:	2.5 mils	nominal	Cured	Arlon SQA-TMS-003
Side 2 (First Pass):	2.5 mils	1.0 mils min.	Uncured	Arlon SQA-TMS-003
Side 2 (Second Pass):	-	-	-	Arlon SQA-TMS-003
Overall Thickness:	10.0 mils	+/- 1.5 mils	-	Arlon SQA-TMS-003

Dielectric Strength (kV): 4.0 kV minimum Method: Arlon SQA-TMS-020
Ply Adhesion (lb/in): 4.0 lbs/in minimum Method: Arlon-SQA-TMS-011

General

Shelf Life: 6 months from date of manufacture @ 70°F
Recommended Cure Cycle: 15 minutes @ 250°F & 50 psi
Recommended Postcure Cycle: 400°F for 2 hours
Product Operating Temperature: -70°F to 428°F



Arlon Silicones Technology

High Performance Foams
1100 Governor Lea Road | Bear, DE 19701-1998 USA
+1-302-834-2100