

PRODUCT INFORMATION SHEET


Arlon Product Number

44568R016

PRODUCT DESCRIPTION

Design / Construction

Side 1 Interleave: 0.0025" Polyethylene
Side 1 Layer 2: Uncured Silicone rubber
Side 1 Layer 1: Cured Silicone rubber
Substrate: Style 1165 fiberglass
Side 2: Uncured Silicone rubber
Side 2 Interleave: 0.0025" Polyethylene



<u>Rubber Add-On Thickness</u>	<u>Value</u>	
Side 1 Layer 2:	0.0045"	Arlon SQA-TMS-003
Side 1 Layer 1:	0.0020"	Arlon SQA-TMS-003
Side 2:	0.0045"	Arlon SQA-TMS-003
Overall Thickness:	0.0160"	Arlon SQA-TMS-003

Product Color : Red

TYPICAL PROPERTIES

<u>Silicone Properties</u>	<u>Value</u>	<u>Method</u>
Tensile Strength psi	860	Arlon SQA-TMS-008
Elongation %	720	Arlon SQA-TMS-008
Tear Strength (Die B) lb/in	115	Arlon SQA-TMS-029
Durometer Shore A Points	39	Arlon SQA-TMS-014
Specific Gravity ---	1.21	Arlon SQA-TMS-024

<u>Substrate Properties</u>	<u>Value</u>	<u>Method</u>
Thickness	0.005"	Arlon SQA-TMS-003
Color	Red	N/A

<u>Product Properties</u>	<u>Value</u>	<u>Method</u>
Bond Strength (S1 to S2) lb/in	9.4	Arlon SQA-TMS-011
Total Product Weight oz/yd ²	15.42	Arlon SQA-TMS-025

SHELF LIFE & PROCESSING RECOMMENDATIONS

Product Shelf Life 6 months from date of manufacture @ 70°F
Note: Shelf life is defined as the duration of time for which the product will meet the physical characteristics outlined on this page. It does not guarantee the product's usefulness in all applications.

Recommended Cure Cycle 15 minutes @ 350°F and 50 psi

Recommended Post Cure Cycle 400°F for 2 hours

Product Operating Temperature -70°F to 428°F

*The data presented in this document represent typical values for the production material.
The data should not be used to write, or in place of, material specifications.
Please verify that any printed hard copy of this datasheet is current by referencing:
<http://www.rogerscorporation.com>*