


ARLON® FLEX HEATER SUBSTRATE SPECIFICATION

Item Number: 55109R030
Description: Flexible Heater Substrate
 Silicone Rubber Calendered onto Fiberglass

Design / Construction



Substrate: 55 Plain Weave Fiberglass (16 mil nominal)
 Silicone Rubber Compound: 10 Compound
 Color: Red

Interleave (Top): LDPE
 Interleave (Bottom):

	<u>Rubber Add-on</u>	<u>Tolerance</u>	<u>Cure State</u>	<u>Method</u>
Side 1:	-	-	-	Arlon SQA-TMS-003
Side 2 (First Pass):	6.0 mils	nominal	Cured	Arlon SQA-TMS-003
Side 2 (Second Pass):	8.0 mils	4 mils min.	Uncured	Arlon SQA-TMS-003
Overall Thickness:	30.0 mils	+/- 3.0 mils	-	Arlon SQA-TMS-003

Dielectric Strength (kV): 9.0 kV Minimum Method: Arlon SQA-TMS-020
 Ply Adhesion (lb/in): 5.0 lbs/in Minimum Method: Arlon-SQA-TMS-011

General

Shelf Life: 6 months from date of manufacture @ 70°F
 Recommended Cure Cycle: 15 minutes @ 250°F & 50 psi
 Recommended Postcure Cycle: 400°F for 2 hours
 Product Operating Temperature: -70°F to 428°F



Arlon Silicones Technology

High Performance Foams
 1100 Governor Lea Road | Bear, DE 19701-1998 USA
 +1-302-834-2100