

ARLON[®] FLEX HEATER SUBSTRATE SPECIFICATION

Item Number: 99140R015
Description: Flexible Heater Substrate
Silicone Rubber Calendered onto Coated Stock

Design / Construction



Substrate: 99 PFTE Coated Stock
Silicone Rubber Compound: 14 Compound
Color: Red

Interleave (Top): LDPE
Interleave (Bottom):

	<u>Rubber Add-on</u>	<u>Tolerance</u>	<u>Cure State</u>	<u>Method</u>
Side 1:	-	-	-	Arlon SQA-TMS-003
Side 2 (First Pass):	-	-	-	Arlon SQA-TMS-003
Side 2 (Second Pass):	-	-	-	Arlon SQA-TMS-003
Overall Thickness:	15.0 mils	+/- 1.5 mils	Uncured	Arlon SQA-TMS-003

UL Information (if applicable):

UL File #: E54153
UL 746 RTI (Elec): 200°C
UL 746 RTI (Str): 200°C
HWI: 4
HAI: 1
CTI: 0
HVTR: 0

General

Shelf Life: 6 months from date of manufacture @ 70°F
Recommended Cure Cycle: 15 minutes @ 250°F & 50 psi
Recommended Postcure Cycle: 400°F for 2 hours
Product Operating Temperature: -70°F to 428°F



Arlon Silicones Technology

High Performance Foams

1100 Governor Lea Road | Bear, DE 19701-1998 USA
+1-302-834-2100