



Arlon Silicones Technology

1100 Governor Lea Road, Bear, DE 19701  
1.302.834.2100 • 1.302.834.4021 (Fax)

## PRODUCT INFORMATION SHEET

**Arlon Product Number** 910-10X ## -P1

### PRODUCT DESCRIPTION

1 inch wide, 10 mil thick, Grey, Rectangular cross-section self-fusing silicone tape.  
Product is supplied in various roll lengths. ## in the product number indicates roll length in yards.

Meets U.S. Military Specification A-A-59163 (supercedes Mil-I-46852C) except for packaging and sampling. The following tests are conducted on one roll from each lot of tape: Thickness, Width, Bond Strength, Tensile Strength, Elongation, Dielectric Strength, and Water Absorption.

#### Design / Construction

**Interleave:** 3 mil PE

**Rubber:** Cured self-fusing silicone rubber

**Cross-Section:** 1" wide Rectangular



#### Rubber Thickness

**Rubber:**

#### Value

10 mil

#### Method

Arlon SQA-TMS-003

**Product Color :** Gray

### PHYSICAL PROPERTIES

#### Silicone Compound Physical Properties

		<u>Value</u>	<u>Method</u>
<b>Tensile Strength</b>	psi	1085	ASTM D 412
<b>Elongation</b>	%	495	ASTM D 412
<b>Durometer</b>	Shore A Points	55	ASTM D 2240
<b>Specific Gravity</b>	---	1.17	Arlon SQA-TMS-024

#### Product Physical Properties

		<u>Value</u>	<u>Method</u>
<b>Dielectric Strength</b>	volts/mil	763	ASTM D 149
<b>Bond Strength</b>	lb/in	2.3	Arlon SQA-TMS-015
<b>Water absorption</b>	%	1.1	Arlon SQA-TMS-016

### SHELF LIFE & PROCESSING RECOMMENDATIONS

**Product Shelf Life** 12 months from DOM @ 75°F

*Note: Shelf life is defined as the duration of time for which the product will meet the physical characteristics outlined on this page.  
It does not guarantee the product's usefulness in all applications.*

**Product Operating Temperature** -60 to +400°F

*The data presented in this document represent typical values for the production material.  
The data should not be used to write, or in place of, material specifications.  
Please verify that any printed hard copy of this datasheet is current by referencing:  
<http://www.rogerscorporation.com/Library/datasheets.htm>*

Last Revised May 11, 2016.