



Arlon Silicones Technology

1100 Governor Lea Road, Bear, DE 19701
1.302.834.2100 • 1.302.834.4021 (Fax)

PRODUCT INFORMATION SHEET

Arlon Product Number T3030-R012

PRODUCT DESCRIPTION

Design / Construction

Side 1: Cured self-fusing silicone rubber
Substrate: 25% Sinusoidal fiberglass
Side 2: Cured self-fusing silicone rubber
Interleave: 0.001" Mylar film



Rubber Thickness

	<u>Value</u>	<u>Method</u>
Width	3.0"	Arlon SQA-TMS-012
Overall Thickness:	0.030"	Arlon SQA-TMS-012

Product Color : Red

TYPICAL PROPERTIES

Product Properties

	<u>Value</u>	<u>Method</u>
Tensile Strength psi	2472	Arlon SQA-TMS-048
Elongation %	31	Arlon SQA-TMS-048
Durometer Shore A Points	50	Arlon SQA-TMS-014
Specific Gravity ---	1.2	Arlon SQA-TMS-024
Dielectric Strength volts/mil	621	Arlon SQA-TMS-020
Adhesion Strength lb/in	10	Arlon SQA-TMS-047

SHELF LIFE AND RECOMENDED OPERATING TEMPERATURE

Product Shelf Life 12 months from DOM @ 70°F

Note: Shelf life is defined as the duration of time for which the product will meet the physical characteristics outlined on this page. It does not guarantee the product's usefulness in all applications.

Product Operating Temperature -60 to +400°F

*The data presented in this document represent typical values for the production material.
 The data should not be used to write, or in place of, material specifications.
 Please verify that any printed hard copy of this datasheet is current by referencing:
<http://www.rogerscorporation.com>*

Last Revised May 14, 2016..