

**/// Datasheet**

# RO4835™ Laminate Data Sheet

## High Frequency Circuit Materials

Thermoset laminate materials, including FR-4, are affected by oxidation over time and temperature. This can slightly increase the dielectric constant and dissipation factor of the circuit substrate. The change rate and impact on circuit performance vary based on design and operating temperature. Rogers' RO4835™ laminate, part of the RO4000® series, offers enhanced stability at high temperatures and is more resistant to oxidation than other hydrocarbon materials. RO4835 laminates share similar electrical and mechanical properties with RO4350B™ laminates and are designed for high frequency performance and cost-effective circuit fabrication. It uses standard epoxy/glass (FR-4) processes and is competitively priced.

For frequencies above 500 MHz, RO4000 materials are ideal due to their low dielectric loss, making them suitable for RF microwave circuits and controlled impedance transmission lines. The material's thermal coefficient of expansion (CTE) matches copper, ensuring excellent dimensional stability and reliable plated through-hole quality in mixed dielectric multi-layer boards, even under thermal shock. RO4000 laminates have a Tg of >280°C (536°F), ensuring stable expansion characteristics throughout circuit processing temperatures.

RO4000 series laminates can be processed using standard FR-4 techniques without specialized via preparation. They are rigid, thermoset laminates, compatible with automated systems and scrubbing equipment for copper surface preparation. RO4835 laminates are RoHS compliant and suitable for UL 94V-0 certified applications.



**/// Standard Offerings**

Standard Thicknesses	Standard Panel Sizes	Standard Cladding
0.0066" (0.17mm) +/- 0.0007"	12" X 18" (305 X 457 mm)	Electrodeposited Copper Foil 1/2 oz. (18µm) 1 oz. (35µm)
0.010" (0.25mm) +/- 0.0010"	24" X 18" (610 X 457 mm)	
0.020" (0.51mm) +/- 0.0015"	24" X 36" (610 X 915 mm)	
0.030" (0.76mm) +/- 0.0020"	48" X 36" (1219 X 915 mm)	
0.060" (1.52mm) +/- 0.0040"		

\*Contact Customer Service or Sales Engineering to inquire about other available product configurations including additional thicknesses, panel sizes and claddings.

**/// Features and Benefits:**

Significantly improved oxidation resistance compared to typical thermoset microwave materials

- Designed for performance sensitive, high volume applications.

Low loss

- Excellent electrical performance allows application with higher operating frequencies.
- Ideal for automotive applications.

Tight dielectric constant tolerance

- Controlled impedance transmission lines

Lead-free process compatible

- No blistering or delamination

Low Z-axis expansion

- Reliable plated through holes

Low in-plane expansion coefficient

- Remains stable over an entire range of circuit processing temperatures

CAF resistant

**/// Typical Applications:**

- Automotive Radar and Sensors
- Point-to point Microwave
- Power Amplifiers
- Phased - Array Radar
- RF Components

### Standard Properties Table

Properties	Typical Value	Units	Test Conditions		Test Method
<b>Electrical Properties</b>					
Dielectric Constant (Process) <sup>1</sup>	3.48 ± 0.05	-	23°C	10 GHz	IPC TM-650 2.5.5.5
Dielectric Constant (Design) <sup>2</sup>	3.66	-	-	8 - 40 GHz	Differential Phase Length
Dissipation Factor	0.0037	-	23°C	10 GHz	IPC TM-650 2.5.5.5
Thermal Coefficient of Dielectric Constant	+50	ppm/°C	-50°C to 150°C		IPC TM-650 2.5.5.5
Volume Resistivity	5 X 10 <sup>8</sup>	MΩ·cm	Condition A		IPC-TM-650, 2.5.17.1
Surface Resistivity	7 X 10 <sup>8</sup>	MΩ			
Electrical Strength (dielectric strength)	30.2 (755)	KV/mm (V/mil)	-		IPC TM-650 2.5.6.2
<b>Thermal Properties</b>					
Decomposition Temp (Td)	390	°C TGA	-		ASTM D3850
Glass Transition Temp (Tg)	>280	°C TMA	A		IPC-TM-650 2.4.24.3
Coefficient of Thermal Expansion - x	10	ppm/°C	-55°C to 288°C		IPC TM-650 2.4.41
Coefficient of Thermal Expansion - y	12				
Coefficient of Thermal Expansion - z	31				
Thermal Conductivity	0.66	W/(m·K)	80°C		ASTM C518
Dimensional Stability (x,y)	<0.5	mm/m (mils/in)	after etch	+E2/150°C	IPC TM-650 2.4.39a
<b>Mechanical Properties</b>					
Copper Peel Strength	0.88 (5.0)	N/mm (pli)	After solder float 35 μm ED foil		IPC TM-650 2.4.8
Young's Modulus	7780 (1128)	MPa (kpsi)	RT		ASTM D638
Tensile Strength	136 (19.7)	MPa (kpsi)	RT		ASTM D638
Flexural Strength	186 (27)	MPa (kpsi)			IPC-TM-650 2.4.4
<b>Physical Properties</b>					
Flammability	V-0	-	-		UL 94
Moisture Absorption	0.05	%	50°C	48 Hr	ATSM D570
Density	1.92	g/cm <sup>3</sup>	23°C		ASTM D792
Lead Free Process compatible	YES	-	-		-

<sup>1</sup> The IPC clamped stripline method can potentially lower the actual dielectric constant due to presence of airgaps between the laminates under test and the resonator card. Dielectric constant in practice may be higher than the values listed.

<sup>2</sup> The design Dk is an average number from several different tested lots of material and on the most common thickness/s. If more detailed information is required, please contact Rogers Corporation. Refer to Rogers' technical paper "Dielectric Properties of High Frequency Materials" available at <http://www.rogerscorp.com>

Typical values are a representation of an average value for the population of the property. For specification values contact Rogers Corporation.

\\\ 100 S. Roosevelt Avenue \\\ Chandler, AZ 85226 \\\ Tel: 480-961-1382 \\\ Fax: 480-961-4533 \\\ [www.rogerscorp.com](http://www.rogerscorp.com)

The information in this data sheet is intended to assist you in designing with Rogers' circuit materials. It is not intended to and does not create any warranties express or implied, including any warranty of merchantability or fitness for a particular purpose or that the results shown on this data sheet will be achieved by a user for a particular purpose. The user should determine the suitability of Rogers' circuit materials for each application. These commodities, technology and software are exported from the United States in accordance with the Export Administration regulations. Diversion contrary to U.S. law prohibited.

The Rogers' logo, Helping power, protect, connect our world, RO4000, RO4350B and RO4835 are trademarks of Rogers Corporation or one of its subsidiaries.

©2024 Rogers Corporation, Printed in U.S.A., All rights reserved.

Revised 1686 011924 Publication #92-160