

BISCO® L3-XX40

BISCO® L3-XX40 is a medium density, cellular silicone foam material designed for use as a vibration isolation pad in rail car floating floors. It insulates, seals, absorbs and protects. Material is available in continuous rolls in a variety of thicknesses.

Features & Benefits, applicable to all BISCO® Cellular Materials:

- Excellent vibration isolation and dampening
- Low smoke evolution
- Low flame spread
- Handles extreme temperatures
- UV and weather resistant

PROPERTY	TEST METHOD	TYPICAL VALUE*	SPECIFICATION**
PHYSICAL			
Color	Visual	Boilermaker Red	---
Thickness, mm (inches)	Internal	4 - 12 (0.157 - 0.472)	See "Width Tolerance" table
Density, kg/m ³ (lb./ft ³)	Internal	352 (22)	296 - 473 (18.5 - 29.5)
Compression Force Deflection, kPa (psi)	ASTM D1056	76 (11)	62 - 124 (9 - 18)
Compression Set, %	ASTM D1056 100°C (212°F) / 22 hrs / 50%	2.4	< 5
Water Absorption, %	Internal 2" below water surface / 24 hrs / change in weight	0.5	< 5

Additional industry specifications tested in tables below.

PROPERTY	TEST METHOD	TYPICAL VALUE*	SPECIFICATION**
FLAMMABILITY			
Flame Spread Index (Is)	ASTM E162	Meets	Flaming Mode < 35
Smoke Density (Ds)	ASTM E662	Meets	Flaming Mode, 1.5 min, < 100 Flaming Mode, 4.0 min, < 100

PROPERTY	TEST METHOD	TYPICAL VALUE*	SPECIFICATION**
THERMAL			
Temperature Range, °C (°F)	Internal	-55 to +200 (-67 to +392)	---
Low Temperature Brittleness	ASTM D746 -55°C (-67°F) / 3 min	---	Pass

Standard Thickness Tolerances

NOMINAL THICKNESS	TOLERANCE
mm (inches)	mm (inches)
4 (0.157)	± 0.48 (± 0.019)
6 (0.236)	± 0.72 (± 0.028)
10 (0.394)	± 1.20 (± 0.047)
12 (0.472)	± 1.44 (± 0.057)

Other thicknesses available upon request

Slit Material and Tape (PSA) Width Tolerances

NOMINAL WIDTH	TOLERANCE
mm (inches)	mm (inches)
> 0 - 76 (> 0 - 3)	± 1.60 (± 0.063)
> 76 - 203 (> 3 - 8)	± 2.39 (± 0.094)
> 203 - 305 (> 8 - 12)	± 3.18 (± 0.125)
> 305 - 457 (> 12 - 18)	± 4.78 (± 0.188)
> 457 - 660 (> 18 - 26)	± 5.56 (± 0.219)
> 660 - 914 (> 26 - 36)	+ 25.4/- 0 (+ 1/- 0)

SPECIFICATIONS

- NFPA 130
- EN45545 - R10 HL3

Notes:

*Typical Value - Value is based on historical data. Please note the frequency of testing varies.

**Specification - Applies to physical properties only, which are based on Rogers' internal benchmark and standard BISCO specification values.

Additional industry specifications are available as well. Specification values in bold are tested on a batch basis. All other properties, flammability, thermal, etc, are based on industry standard guidelines.

To order BISCO materials, please contact our Sales Specialists at 860.928.3622 or via email at EMS_CT_cust_serv@rogerscorporation.com



The information contained in this Data Sheet is intended to assist you in designing with Rogers' BISCO Silicone Foams. It is not intended to and does not create any warranties, express or implied, including any warranty of merchantability or fitness for a particular purpose or that the results shown on the Data Sheet will be achieved by a user for a particular purpose. The user should determine the suitability of Rogers' BISCO Silicone Foams for each application. The Rogers logo, BISCO logo and BISCO are trademarks of Rogers Corporation or one of its subsidiaries. © 2009, 2016, 2023 Rogers Corporation, All rights reserved. Printed in U.S.A., 0123-PDF, Publication #180-319 www.rogerscorp.com