

PORON[®] 4701-30 Very Soft (Supported)

Based on Global Test Methods

PROPERTY	TEST METHOD	TYPICAL VALUE	
PHYSICAL			
Density, kg/m ³ (lb./ft ³)	ASTM D3574-95, Test A	320 (20)	400 (25)
Tolerance, %		± 10	
Thickness, mm (inches)		1.63 (0.064)	0.53 (0.021)
		2.41 (0.095)	0.94 (0.037)
			1.19 (0.047)
Tolerance, %		± 10	± 15
Standard Color (Code)		Black (04)	
Compression Force Deflection, kPa (psi)	ISO 6916-1 30mm/min Strain Rate Force Measured @ 25% Deflection	41 (6)	-
Compression Set, % max	ISO 1856 Test A @ 70°C (158°F)	1.9	-
Dimensional Stability, % max change	22 hrs @ 80°C (176°F) in a Forced-Air Oven		± 1
ELECTRICAL			
Dielectric Strength, kV/mm	IEC 243-1	3.8	-
Volume Resistivity, ohm-cm	IEC 60093	1.91E +13	-
Surface Resistivity, ohm/sq	IEC 60093	4.19E +15	-
TEMPERATURE RESISTANCE			
Recommended Constant Use, max.	UL 157	90°C (194°F)	-
Recommended Intermittent Use, max.	UL 157	121°C (250°F)	-
Embrittlement	ISO 974 (E)	-55°C (-67°F)	-

PROPERTY	TEST METHOD	TYPICAL VALUE	
FLAMMABILITY AND OUTGASSING		320 (20)	400 (25)
Flammability, mm (inches)	UL 94HBF [†] (File E20305) Min. Thickness Passed, mm (in)	-	-
	ISO 3795, DIN 75200 Min. Thickness Passed, mm (in) Max. Burn Rate (mm/min)	2.41 (0.095) 75	-
	FMVSS 302 (Pass ≥) Min. Thickness Passed, mm (in)	-	-
Fogging	ISO 6452, DIN 75201	PASS	-
ENVIRONMENTAL			
Gasketing & Sealing	UL JMST2 (Consisting of UL50 & UL508)	File MH15464	

Notes:

†Designed to meet UL 94 HBF based upon 2022 test criteria. As of 2023 items with nominal density $\geq 15.6\text{lb/ft}^3$ (250kg/m³) are no longer eligible to be tested for UL 94 HBF but remain equivalent.

- - Represents testing not available at this time.
- All metric conversions are approximate.
- Additional technical information is available.
- Typical values should not be used for specification limits.

For more information and to request a sample, please contact our team of experts at solutions@rogerscorp.com