

Typical Product Properties

PORON® Polyurethanes

PORON® 4790-79SE-20006/20008-04 - Data Sheet - *Preliminary*

PROPERTY		TEST METHOD	VALUE	
Foam	Description		79SE-20006	79SE-20008
	Density, kg/m³ (lb./ft ³)	ASTM D 3574-95 Test A	320 (20)	
	Tolerance		± 10%	
	Thickness, mm (FAL + foam) (inches)	With digital tester (ONO SOKKI)	0.15 (0.006)	0.20 (0.008)
	Tolerance		± 15%	
	Standard Color (Code)		Black (04)	
Compression Force Deflection, Kpa (psi)	Modified ASTM D 3574: PTP-0033 at 25% deflection	7~28 1~4		

PROPERTY		TEST METHOD	UNIT	VALUE
Supported Adhesive	Peel Adhesion	JIS Z0237 8	N/25mm	3.9
	Release Adhesion	ASTM D 1000 180° Peel	N/25mm	6.5
	Tack	JIS Z0237 12	#	5
	Thickness		mm	0.011
	Shelf Life	From date of manufacture	Months	12

The information contained in this data sheet is intended to assist you in designing with Rogers' Elastomeric Material Solutions. It is not intended to and does not create any warranties, express or implied, including any warranty of merchantability or fitness for a particular purpose or that the results shown on the data sheet will be achieved by a user for a particular purpose. The user should determine the suitability of Rogers' PORON Polyurethane Materials for each application. The Rogers logo, Helping power, protect, connect our world and PORON are trademarks of Rogers Corporation or one of its subsidiaries. © 2017 Rogers Corporation, All rights reserved. Printed in U.S.A. 0317-PDF Publication #17-364